

[Biofouling](#). 2010 Apr;26(3):359-65.

The effects of copper additives on the quantity and cell viability of adherent *Staphylococcus epidermidis* in silicone implants.

[Gosau M](#), [Prantl L](#), [Feldmann M](#), [Kokott A](#), [Hahnel S](#), [Burgers R](#).

Department of Cranio-Maxillo-Facial Surgery, University Medical Center, Regensburg, Germany.

martin.gosau@klinik.uni-regensburg.de

This in vitro study evaluated the antibacterial effect of copper additives in silicone implants. Specimens of a standard silicone material used in breast augmentation and modified copper-loaded silicone specimens were prepared and incubated in a *Staphylococcus epidermidis* suspension (2 h, 37 degrees C). After the quantification of adhering staphylococci using a biofluorescence assay (Resazurin), the viability of the adhering bacterial cells was quantified by live or dead cell labeling in combination with fluorescence microscopy. In the Resazurin fluorometric quantification, a higher amount of adhering *S. epidermidis* cells was detected on pure silicone (4612 [2319/7540] relative fluorescence units [rfu]) than on silicone with copper additives (2701 [2158/4153] rfu). Additionally, a significantly higher amount of adhering bacterial cells (5.07% [2.03%/8.93%]) was found for pure silicone than for silicone with copper additives (1.72% [1.26%/2.32%]); ($p < 0.001$). Calculations from live or dead staining showed that the percentage of dead *S. epidermidis* cells adhered on pure silicone (52.1%) was significantly lower than on silicone with copper additives (79.7%); ($p < 0.001$). In vitro, silicone material with copper additives showed antibacterial effects against *S. epidermidis*. Copper-loaded silicone may prevent bacterial colonization, resulting in lower infection rates of silicone implants.